

AMORPHOUS GRAPHITE

Graphit Kropfmühl GmbH
 Langheinrichstraße 1 | 94051 Hauzenberg | Germany
 +49 8586 609-0 | sales@gk-graphite.com

GRAPHITE GRADE	CARBON CONTENT [IN %]	ASH [IN %]	PARTICLE SIZE
AM 515	min. 75	max. 25	min. 85% < 75µm (200 mesh)
AM 517	min. 75	max. 25	min. 85% < 45µm (325 mesh)
AM 506	min. 80	max. 20	min. 85% < 75µm (200 mesh)
AM 505	min. 80	max. 20	min. 85% < 45µm (325 mesh)
AM 563	min. 85	max. 15	min. 85% < 75µm (200 mesh)
AM 562	min. 85	max. 15	min. 85% < 45µm (325 mesh)
AM 561	min. 90	max. 10	min. 85% < 75µm (200 mesh)

Packaging: 25 kg paper bag / 40 x 25 kg pallet / 1 to big bag

